







Graphitqualitäten für die Funkenerosion

[graphite grades for EDM]

Eigenschaft [properties]	Einheit [unit]	Schrupp	Universal		Feingraphit		Superfein
		CP-1000	CP-1100	CP-1200	CP-1300	CP-1400	CP-1500
Korngröße [grain size]	μØ	12	7	5	4	3	3
Dichte [bulk density]	g/cm ³	1,80	1,83	1,85	1,87	1,93	1,88
Härte [hardness]	shore	60	66	68	68	83	75
Spez. elektr. Widerstand [electrical resistivity]	μ OHM m	13,0	15,0	15,0	14,5	15,0	17,5
Biegebruchfestigkeit [bending strenght]	Mpa (N/mm ²)	50	54	61	61	74	95
Druckfestigkeit [compressive strenght]	MPa (N/mm ²)	103	114	113	137	176	190
Zugfestigkeit [tensile strength]	MPa (N/mm ²)	33	35	40	40	48	n/a
Ausdehn. koeffizient [coeff. of thermal expansion]	K x 10 ⁻⁶ /°C	5,0	5,0	5,4	5,6	6,0	5,3
Wärmeleitfähigkeit [thermal conductivity]	W/m°K	105	105	93	90	90	n/a
Youngs´ s Modulus [elastic modulus]	GPa (kN/mm ²)	9,1	10,8	11,5	13,5	14,2	12,6
Aschegehalt [ash content]	%	0,05	0,05	0,10	0,10	0,10	0,10
Blockabmessungen [block dimensions]	mm	1020 x 630 x 350	1020 x 630 x 350 1020 x 510 x 270	1020 x 630 x 350 1020 x 510 x 270	950 x 380 x 155	620 x 305 x 70	1000 x350 x140
Struktur [structure]	x100						

Angegebene Daten sind Mittelwerte welche sich geringfügig verändern können.
[The values of physical properties shown above are approximate.]

Erreichbare Oberflächengüten

[surface finishing]

VDI 3400	12	15	18	21	24	27	30	33	36	39	42	45
Ra μm	0,40	0,56	0,80	1,12	1,60	2,24	3,15	4,50	6,30	9,00	12,50	18,00
Ra μin	16	22	31	44	63	88	124	177	248	354	492	709
								CP-1000				
						CP-1100						
				CP-1200								
			CP-1300 / 1400									
		CP-1500										

CP-Handels-GmbH

Konrad-Adenauer-Str. 84
D-53343 Wachtberg

Telefon +49 (0) 228.391879 -0
Telefax +49 (0) 228.391879 -9

E-Mail: info@graphithandel.de
Internet: www.graphithandel.de